

UNIPOL V 2155

Unipol V 2155 is a plasticizer-free aqueous copolymer emulsion based on vinyl acetate, acrylic esters and the vinyl ester of a long chain branched carboxylic acid.

	Unit	Value	Method
Sales Specifications			
Solids content	%	55 ± 1	DIN 53189 / ISO 1625
Viscosity	mPa·s	3000 ± 1500	ISO 2555, Brookfield RVT; spindle 3; 20 rpm; 23 °C
pH		4.5 ± 1	DIN 53785 / ISO 1148
Typical values of emulsion			
Particle size	µm	0.50 - 0.80	
Minimum film forming temperature (MFFT)	°C	approx. 9	DIN 53787 / ISO 2115
Density	g/cm ³	approx. 1.04	ISO 8962
Typical values of film¹			
Appearance		Clear, tough	
Density	g/cm ³	1.10	with reference to DIN 53479
Water absorption	%		with reference to DIN 53495
Tensile Strength	Nmm ²		with reference to DIN 53455
Glass transition temperature (T _g)	°C	approx. 19	DIN 53765 (DSC; heating rate 10 K/min)

(1) Dried in standard conditioning atmosphere at 23 °C and 50 % relative humidity (DIN EN 23270)

Applications

Architectural decorative interior and exterior coatings	Primers
Vinyl Silk Paints	Clear Coatings

Specific Information

Unipol V 2155 exhibits very good pigment binding power. It is especially suitable for high quality exterior and interior paints which exhibit very high resistance to water and outstanding scrub resistance and adhesion properties.

Unipol V 2155 is designed to give very good rheological profile to the final paint, ensuring very good brush application, flow and levelling properties. Its molecular weight and particle size distribution make it an ideal choice for formulating with rheology modifiers and results in consistent paint manufacturing.

Storage

Unipol V 2155 can be stored for at least 6 months between +5°C and +40°C.

Packaging

Unipol V 2155 is available in 120 kg drums, 1.050 kg IBCs and bulk.

The information contained in this publication is based on our current information and experience and is to the best of our knowledge. Acro-pol does not make any warranty, express or implied, or accepts any liability in connection with this information. This information is for use by technically skilled persons at their own discretion and risk. The user alone has the responsibility to ensure that existing laws and legislation are observed when using the product.